

**VINTAGE**

1	DESCRIPTION
	Enamel mosaic, consisting of 25x25mm tiles, 4 mm thickness. Vintage mosaic tiles deliberately present small imperfections with uneven edges, faded colours and rough surfaces, giving the product its unique look.

2	USES
A	INTERIOR WALLS walls and ceilings in general, for residential and public buildings
B	FLOORING Light traffic (private residential rooms)
C	- EXTERNAL WALLS - SWIMMING POOLS - HUMID AREAS (shower, turkish bath, bio sauna...) Suitable for these areas

3	WEIGHTS AND MEASUREMENTS
	Size 25x25mm
	Mounting paper
	Sheet dimensions 313,2x313,2 mm
	Number of tiles/sheet 144
	Thickness 4 mm
	Joint 0÷1,2 mm
	Weight 7,8 kg/sqm
	Quantity/carton 0,98 sqm
	Sheets/carton 10

4	TECHNICAL CHARACTERISTICS																																								
	<table border="1"> <thead> <tr> <th>Description</th> <th>Test</th> <th>Established limits</th> <th>Result</th> </tr> </thead> <tbody> <tr> <td>Water absorption</td> <td>ISO 10545 - 3</td> <td>E ≤ 0.5%</td> <td>&lt; 0.5</td> </tr> <tr> <td>Wear resistance (PEI)</td> <td>ISO 10545 - 7</td> <td>Class 0 - 5</td> <td>Class 2</td> </tr> <tr> <td>Resistance to chemical attack</td> <td>ISO 10545 -13</td> <td></td> <td>resistant</td> </tr> <tr> <td>Frost resistance</td> <td>ISO 10545 - 12</td> <td></td> <td>resistant</td> </tr> <tr> <td>Colours' resistance to fading</td> <td>DIN 51094</td> <td></td> <td>resistant</td> </tr> <tr> <td>Stain resistance</td> <td>ISO 10545 - 14</td> <td></td> <td>resistant</td> </tr> <tr> <td>Resistance to thermal shocks</td> <td>ANSI A 137.2-2012</td> <td>+15/+71°C</td> <td>resistant</td> </tr> <tr> <td>Slip resistance</td> <td>DIN 51097</td> <td>A(12°-18°) B(18°-24°) C(+24°)</td> <td>A</td> </tr> <tr> <td>Slip resistance</td> <td>DIN 51130</td> <td>R9 - R13</td> <td>R9</td> </tr> </tbody> </table>	Description	Test	Established limits	Result	Water absorption	ISO 10545 - 3	E ≤ 0.5%	< 0.5	Wear resistance (PEI)	ISO 10545 - 7	Class 0 - 5	Class 2	Resistance to chemical attack	ISO 10545 -13		resistant	Frost resistance	ISO 10545 - 12		resistant	Colours' resistance to fading	DIN 51094		resistant	Stain resistance	ISO 10545 - 14		resistant	Resistance to thermal shocks	ANSI A 137.2-2012	+15/+71°C	resistant	Slip resistance	DIN 51097	A(12°-18°) B(18°-24°) C(+24°)	A	Slip resistance	DIN 51130	R9 - R13	R9
Description	Test	Established limits	Result																																						
Water absorption	ISO 10545 - 3	E ≤ 0.5%	< 0.5																																						
Wear resistance (PEI)	ISO 10545 - 7	Class 0 - 5	Class 2																																						
Resistance to chemical attack	ISO 10545 -13		resistant																																						
Frost resistance	ISO 10545 - 12		resistant																																						
Colours' resistance to fading	DIN 51094		resistant																																						
Stain resistance	ISO 10545 - 14		resistant																																						
Resistance to thermal shocks	ANSI A 137.2-2012	+15/+71°C	resistant																																						
Slip resistance	DIN 51097	A(12°-18°) B(18°-24°) C(+24°)	A																																						
Slip resistance	DIN 51130	R9 - R13	R9																																						

<b>5</b>	<b>STRENGTHS</b>
	<ul style="list-style-type: none"> <li>- ease of surface cleaning</li> <li>- light weight and thinness allow for easy renovations</li> <li>- the reduced format makes it suitable for tiling curved surfaces 25x25 mm tiles glued on paper: convex surfaces, 30 mm radius - concave surfaces, 50 mm radius</li> </ul>

<b>6</b>	<b>INSTALLATION</b>
<b>A</b>	<p>For best results, the foundation must have a perfectly smooth, even surface, and must be dry, sound and stable.</p> <ul style="list-style-type: none"> <li>- Cement or plaster foundations: recommended use of adhesive Bisazza Ad Hoc</li> <li>- Foundations of other nature: recommended use of adhesive Bisazza eGlue</li> <li>- For exteriors, submersed areas and humid areas: recommended use* of adhesive Bisazza Ad Hoc+Ultra</li> <li>- Installation in swimming-pools with salty water or thermal water: recommended use of Bisazza Installation Kit (Bisazza eGlue + Fillgel Plus UVR); we recommend waterproofing with epoxy products as well.</li> <li>- Thoroughly wash traces of paper glue before grouting</li> <li>- When laying, use a spatula with 3,5 mm teeth</li> </ul> <p>Average consumption Bisazza Ad Hoc: 1.2 kg/sqm (two coats of skimming included) Average consumption Bisazza Ultra: 0.8 kg/sqm Average consumption Bisazza eGlue: 1.6 kg/sqm (please add 0.9 Kg/sqm for the skimming)</p> <p>* except for any specific rule or protocol enforced by the single Country.</p>
<b>B</b>	<p><b>Grouting:</b> For the best results and performance, use Bisazza Fillgel Plus UVR. The grout colour will affect the final aesthetic appearance of the product installed. Being a colourless and semi-transparent grout, Fillgel 1104 neutro base needs to be used with special care. Because of its colourless feature, the yellowing due to UV rays exposure becomes more visible with time. For this reason, Fillgel 1104 neutro base cannot be used outdoors and in outdoor swimming-pools.</p> <p>Average consumption Bisazza FILLGEL PLUS UVR: 1 kg/sqm</p> <p><b>For any information on the installation procedure, consult the installation book and the products technical data sheets.</b></p>

<b>7</b>	<b>MAINTENANCE</b>
	<p>Use ordinary cleaning products for maintenance and cleaning of glass mosaic surfaces (except those containing hydrofluoric acid or phosphoric acid), being careful to rinse thoroughly with water. Alkaline detergents should be used carefully and rapidly rinsed out with water. Any cleaning product should not be used on heated or directly exposed to sunrays surfaces. Avoid using abrasive tools and high pressure jets of water.</p>

<b>8</b>	<b>WARNINGS</b>
	<p>Before the application, all the materials should be stored in a dry place sheltered from rain and humidity. <b>IMPORTANT:</b> the Vintage tiles can't be used in blends and decorations together with other Bisazza Collections tiles.</p>